

MARBOPUR Primer 44

Primer

Application:



Single-component primer (bonding agent) for joints made from sealing compound MARBOPUR 30.
 Many absorbent and non-absorbent surfaces such as stone, concrete and masonry, etc.
 Not suitable for tension cracks endangered plastics such as PMMA / PC.

- Preferably in the floor area
- For outdoors

Properties:

- Single-component
- Good adhesion
- Ready to use
- Low viscosity

Materialbasis:

- Polyurethane

Technical data:

Colour	transparent
Working temperature	+ 5 °C to + 30 °C
Working time	ca. 2 hours
Flashing-off time	30 to 240 minutes (depending on Temperature)

Substrate preparation:

The contact surfaces must be solid, clean, dry and free of grease.
 Old coatings must be removed.

Processing:

Apply the primer evenly with a brush, the application of the layer should be opaque.
 The material and component temperature should be between 5 °C and 30 °C.
 The MARBOPUR 30 sealant can be applied after a flashing-off time of at least 30 minutes to maximum 4 hours.
 If more than 4 hours have elapsed, roughen the primer coat and apply new primer.
 Preliminary tests are recommended if in doubt.

Post-treatment:

Once the primer has been applied, protect it against direct sunshine, excessively fast drying out and driving rain.

Material consumption:

- Packaging unit corresponds to approx. 130 linear metres with a joint dimension 20 x 15 mm

Delivery form:

- 1 l bottle

Storage:

- Store in a cool, dry place
- The unopened original container can be stored for up to 12 months
- Handle broken on containers of 1 month

Disposal:

See safety data sheet.

Safety notes:

- For the handling of chemical substances, the essential, physical, safety, toxicological and ecological data are to be taken from the EC safety data sheet.
- The regulations of the Ordinance on Hazardous Substances must be observed.
- Ensure good ventilation when working.

MARBOPUR Primer 44

Notes:

- The technical data refer to +20 °C and 50 % relative humidity. Lower temperatures lengthen, higher temperatures shorten the specified values.
 - For the work to be performed, the relevant recommendations, guidelines, standards and regulations as well as the generally accepted rules of technology must be taken into account.
 - Keep out of the reach of children.
 - Additional information: see safety data sheet.
-

During the course of the work, comply with the relevant recommendations and guidelines, standards and regulations and well as the applicable leaflets and generally accepted rules of technology. We have no influence over differences in weather, substrate and building conditions. Written and verbal technical application recommendations which we offer as assistance for the purchaser or the processor are non-binding and do not represent a contractual legal relationship or a contractually defined subsidiary obligations. The information and recommendations provided in the technical leaflet relate to the usual application. On publication of this technical leaflet, all previous versions are invalidated. ed 05.01.2021